

## PRODUCT DATA APPROVAL SHEET

Core- T0903

Cosmo Ferrites Ltd. - INDIA

**Appearance & Shape:** To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards. **Effective Parameters irrespective of material grade (per piece)** 

Effective Length (L<sub>e</sub>): 20.7mm
Effective Area (A<sub>e</sub>): 7.3mm<sup>2</sup>
Effective Area (A<sub>Min</sub>): 7.3mm<sup>2</sup>
Effective Volume (V<sub>e</sub>): 151mm<sup>3</sup>
Approximate weight: 0.8g




## T0903 Coated (Green)

Test Conditions: 10kHz/150mV/N=01/Lo=Zero/25°C

Material Grade	Initial Permeability (μ <sub>iac</sub> )	AL Value (nH)	Approx.μ <sub>e</sub>	D.Strength (kV)	Ordering code
CF191	4300 ±20%	1900 +30%/-20%	≈4300	≥1.0	CF191T0903 C

## **Dimensions(Un-coated Core)**

Dimension	Nominal	Maximum	Minimum
	(in mm)	(in mm)	(in mm)
Α	9.53	9.83	9.23
В	4.75	4.95	4.55
С	3.18	3.38	2.98



## **Dimensions(Coated Cores)**

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
Α	-	10.33	-
В	-	-	4.05
С	-	3.88	-

- 1. Coating material for the product is in compliance with RoHS directive 2002/95/EC.
- 2. Ferrite material in compliance with RoHS directive 2002/95/EC.

For Cosmo Ferrites Limited-INDIA

Checked By: A.K. Approved By: B.S. Authorized By: KSR

Date: 06-12-2013(ISSUE NO.1)

Customer's Approval Authorized Signatory:

Name: Date:



Semic Trade, s.r.o. Volutová 2521/18 158 00 Praha 5 Czech Republic www.semic.cz

semic@semic.cz tel.: +420 251 625 331, 332, 377