


## Lj T 1205C - GH10

	DIMENSIONS (mm)	
		Before Coating
	A	$12.7 \pm 0.4$
	B	$7.92 \pm 0.3$
	C	$4.9 \pm 0.3$
		After Coating
	A	13.5max
B	7.4min	
C	5.9max	

EFFECTIVE CORE PARAMETERS				
Cl ( mm <sup>-1</sup> )	Le ( mm)	Ae ( mm <sup>2</sup> )	Ve ( mm <sup>3</sup> )	Weight (g/pcs)
2.71	31.2	11.49	358.8	≈2.4

ITEM	SPEC	Test Coil	Test Condition	Equipment
AL	$4630\text{nH}/\text{N}^2 \pm 30\%$	$\phi 0.35 \times 1\text{T}_s$	1KHz,0.25V $25 \pm 3^\circ\text{C}$	CH3302 or Equal

GDBZ20210626503

